

PHS Apollo Vapour Control Membrane

PHS Apollo Vapour Control Membrane enables airtightness and vapour control in roof and wall constructions.

PHS Apollo Vapour Control has an optimum fixed vapour resistance level of Sd 2m. This allows for an ideal level of vapour control by preventing diffusion of internal vapour into the building envelope back in winter and allowing diffusion in summer.

This prevents a build-up of condensed water vapour within the building envelope, that facilitates mildew growth and constructional damage.

The CE sign according to DIN EN 13984 gives the necessary assurance for the quality of the product.



Technical Data

Mass per unit	100g/m ² , ±10g/m ² , EN1849-2
Resistance to water penetration	Passed, EN13984 (EN1928 Method A)
Water vapour transmission rate	2m, EN1931
Reaction to fire	Class E, EN13501-1
Tensile property max. force (MD)	200N/50mm, ±30N, EN12311-1
Tensile property max. force (CD)	≥120N/50mm, ±30N, EN12311-1
Tensile property elongation (MD)	≥70%, ±15%, EN12311-1
Tensile property elongation (CD)	≥90%, ±15%, EN12311-1
Resistance to tearing (MD)	120N, ±30N, EN12310-1
Resistance to tearing (CD)	160N, ±30N, EN12310-1
Ageing	Passed, EN1296
Alkali resistance	NPD, EN13984
Impact rain test	Passed
Shear resistance of joints	NPD, EN12317-2
Water tightness of seams	NPD
Resistance to impact	NPD, EN12691
Hazardous substances	No
Temperature resistance	-40C/+100C

Size

- 3000mm x 50m,
- Box Quantity: 1.

Application

- Store in dry rooms from +5C to +25C, protected from UV-radiation.
- The membrane should be applied perpendicular to the direction of the application surface i.e. studs, rafters and joists.
- The membrane should be fixed with staples every 150mm or PHS Double Sided Tape.
- PHS Argo joining Tape or a suitable PHS Grommet should be used for penetrations.
- For bonding barrier overlaps, penetrations and repair spots, PHS Argo or a similar tape is recommended.
- For connections to concrete or masonry PHS Internal Adhesive Sealant is recommended.
- Ensure there is a 100mm overlap of the membranes and tape with PHS Argo Tape or another suitable tape.